

Produktbezeichnung	Verglasungsaufbau außen / SZR / innen	U _g Wert [W/m ² K]	LT [%]	g [%]	LR [%]
R+K Sanco plus	4 / 16Ar / :4	1.1	80	60	14
R+K Sanco plus	4 / 14Ar / :4	1.2	80	60	14
R+K Sanco plus	4 / 12Ar / :4	1.3	80	60	14
R+K Sanco plus	4 / 12Kr / :4	1.1	80	60	14
R+K Sanco plus	4 / 10Kr / :4	1.0	80	60	14
R+K Sanco Zero	4 / 16Ar / :4	1.0	71	50	20
R+K Sanco plus 3	4: / 14Ar / 4 / 14Ar / :4	0.6	70	49	18
R+K Sanco plus 3	4: / 12Ar / 4 / 12Ar / :4	0.7	70	49	18
R+K Sanco plus 3	4: / 10Ar / 4 / 10 Ar / :4	0.8	70	49	18
R+K Sanco plus 3	4: / 14Kr / 4 / 14Kr / :4	0.5	70	49	18
R+K Sanco Zero 3	4: / 16Ar / 4 / 16Ar / :4	0.5	57	35	29
R+K Sanco Zero 3	4: / 12Ar / 4 / 12Ar / :4	0.7	57	35	29
R+K Sanco Zero 3	4: / 12Kr / 4 / 12Kr / :4	0.5	57	35	29

Die angegebenen Werte können je nach Hersteller abweichen!